



DRYCAST™

General Recommendation for Use:

Use Consistency (cc/100gms)	19 - 21
Vicat Set Time (minutes)	15 - 25
% Set Expansion	0.15
Dry Density (lbs. / ft ³)	127.5
Expected Compressive Strength (PSI)	13,000

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

Used for art statuary pieces and lamps. Low water demand eliminates the need for drying rooms.

For more information, call 1-888-PLASTER.