



## STATUARY CASTING PLASTER (FINE GRIND)- BR646

### General Recommendation for Use:

Use Consistency (cc/100gms)	62 - 67
Vicat Set Time (minutes)	17 - 23
% Set Expansion	0.18
Dry Density (lbs. / ft <sup>3</sup> )	69 - 73
Expected Compressive Strength (PSI)	3200 - 4200

\*Measured at Use Consistency

\*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

### **Description:**

A white colored, fine grind plaster used for ornamental casting and art novelties.

**For more information, call 1-888-PLASTER.**