



Densite® K-6

General Recommendation for Use:

Use Consistency (cc/100gms)	34 - 35
Vicat Set Time (minutes)	25 - 35
% Set Expansion	0.300 - 0.325
Dry Density (lbs. / ft ³)	102 - 104
Expected Compressive Strength (PSI)	7000 - 8000

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

A longer setting, base Densite® gypsum cement, that provides low consistency in a neutral product.

For more information, call 1-888-PLASTER.