



## INDUSTRIAL MOLDING

### General Recommendation for Use:

Use Consistency (cc/100gms)	70 - 75
Vicat Set Time (minutes)	27 - 37
% Set Expansion	0.15
Dry Density (lbs. / ft <sup>3</sup> )	65 - 69
Expected Compressive Strength (PSI)	1500 - 2000

\*Measured at Use Consistency

\*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

### **Description:**

A fine grind molding plaster for general use.

**For more information, call 1-888-PLASTER.**