



IMPRESSION PLASTER

General Recommendation for Use:

Use Consistency (cc/100gms)	50
Vicat Set Time (minutes)	2 - 3
% Set Expansion	0.20 - 0.21
Dry Compressive Strength (PSI)	4100 - 4500

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

A fine grind high purity white plaster.

For more information, call 1-888-PLASTER.