



MANUFACTURER'S STUCCO

General Recommendation for Use:

Use Consistency (cc/100gms)	65 - 70
Vicat Set Time (minutes)	15 - 25
Dry Density (lbs. / ft ³)	82 - 85
Dry Compressive Strength (PSI)	1800 - 2200

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

A base plaster used for reformulation within the construction compounder industry.

For more information, call 1-888-PLASTER.