

Manufacturer

Georgia-Pacific Gypsum
 133 Peachtree Street
 Atlanta, GA 30303
 Georgia-Pacific Canada
 2180 Meadowvale Boulevard, Suite 200
 Mississauga, ON L5N 5S3
 Technical Service Hotline: 1-800-225-6119

Description

ToughRock® Fireguard X™ Abuse-Resistant Gypsum Board is designed for wall assemblies in high-traffic areas where surface durability and indentation resistance are especially important, such as schools, hospitals, corrections facilities and offices. ToughRock Fireguard X Abuse-Resistant Gypsum Board is specially formulated to offer greater resistance to abrasion, rubbing, scraping, gouging and indentation on the surface.

Georgia-Pacific ToughRock Gypsum Board products are GREENGUARD and GREENGUARD Gold Certified for low emissions of volatile organic compounds (VOCs). They are listed in CHPS® High Performance Product Database as low emitting products.

ToughRock Fireguard X Abuse-Resistant Gypsum Board consists of a noncombustible (per ASTM E136), dimensionally stable gypsum core formed between a face layer of heavy, smooth, abuse-resistant paper and a back layer of heavy liner paper. The heavy-duty face paper is highly resistant to scuffing when sanding joints and fasteners and provides a superior surface for decoration. It readily accepts a wide range of decorative finishes.

The 5/8" (15.9 mm) ToughRock Fireguard X Abuse-Resistant Gypsum Board has a Type X core (per ASTM C1396) that may be used in many fire-rated assemblies.

ToughRock Fireguard X Abuse-Resistant Gypsum Board comes from the factory as a ready-to-finish product. The long edges are tapered. After installation, ends, edges, corners and fastener heads are normally concealed with joint treatment to produce a smooth, seamless surface prior to final decoration.

Advantages

- Highly resistant to abuse. Offers greater resistance to abrasion, gouging and impact on the surface.
- Low installation cost. Easy-to-install; goes up quickly and finishes easily when compared to block construction.
- Classified for fire resistance ratings. Core meets criteria for Type X as defined in ASTM C1396.

Product Specification

ToughRock Fireguard X Abuse-Resistant Gypsum Board is manufactured to meet the requirements of ASTM C1396 Section 5; CSA A82.27-M; Federal Specification SS-L-30D Type III Grade X; abuse resistant when tested in accordance with ASTM C1629; and conforms to the requirements of uniform IBC/IRC building codes pertaining to Type X gypsum board.

Limitations

- ToughRock Fireguard X Abuse-Resistant Gypsum Board is a non-structural product and should not be used as a nailing base to support heavy wall-mounted objects.
- It is intended for interior applications only.
- It must be kept dry and cannot be used where exposure to moisture is extreme or continuous.
- Do not use ToughRock Fireguard X Abuse-Resistant Gypsum Board where there is prolonged exposure to temperatures exceeding 125°F (52°C) and/or continuous exposure to extreme humidity, e.g., adjacent to radiant heating systems, wood-burning stoves, heating appliances, saunas or steam rooms.

Abuse Resistance

Surface Abrasion: Level 2 Tested in accordance with ASTM C1629.
Indentation Resistance: Level 1 Tested in accordance with ASTM C1629.
Soft-body Impact: Level 1 Tested in accordance with ASTM C1629.

Product Applications

ToughRock Fireguard X Abuse-Resistant Gypsum Board shall be applied in accordance with ASTM C840 and GA-216. To apply the product to steel framing, use 20-gauge* or Type S-12 screws for heavier gauge steel. The product also can be applied to wood framing with drywall nails or screws and with special adhesives in combination with supplemental fasteners.

Handling Precautions

Product is heavier than typical 5/8" (15.9 mm) board. Caution must be used when loading and moving board. Store ToughRock Fireguard X Abuse-Resistant Gypsum Board off the ground and under cover. Stack the product flat on a level surface. Use risers to ensure support for the entire length of the board to prevent sagging. As individual sheets are removed for installation, they should be raised up on edge carefully and carried in a vertical position. (Appropriate handling is outlined in Gypsum Association publications GA 216 and GA-801.) Avoid impact, undue flexing and subsequent damage to panel edges, ends and corners.

Handling and Use—Caution

This product may contain fiberglass which may cause skin irritation. Dust and fibers produced during the handling and installation of the product may cause skin, eye and respiratory tract irritation. Avoid breathing dust and minimize contact with skin and eyes. Wear long sleeve shirts, long pants and eye protection. Always maintain adequate ventilation. Use a dust mask or NIOSH/MSHA approved respirator as appropriate in dusty or poorly ventilated areas.

Material Safety Data Sheet

Material Safety Data Sheet (MSDS) is available upon request or online at www.buildgp.com/safetyinfo.

Decoration

ToughRock Fireguard X Abuse-Resistant Gypsum Board should be finished in the same manner as other gypsum board. For detailed finishing instructions, consult the Gypsum Association Publication GA 216, "Recommended Procedure for the Application and Finishing of Gypsum Panel Products," and ASTM C840, "Standard Specification for Application and Finishing of Gypsum Board."

ToughRock Fireguard X Abuse-Resistant Gypsum Board is designed to accept most types of paints, texture and wall covering materials.

Georgia-Pacific Gypsum strongly recommends priming the surface with a full-bodied, quality latex primer before applying a final decorative material. Priming will equalize the suction variation between the joint compounds and the paper surface. If glossy paints are used, a skim coat of trowel-applied joint compound should be applied over the entire surface to reduce highlighting or joint photographing. This method is also recommended in areas with severe natural or artificial side lighting. Joint treatment must be thoroughly dry before proceeding with primer application and final decoration.

Georgia-Pacific Gypsum recommends application of a sealer under wallpaper or other wall covering so that the surface will not be damaged if the covering is subsequently removed during redecorating. For further details, see Gypsum Association GA-214, "Recommended Specification for Levels of Gypsum Board Finish."

Technical Data—Surface Burning Characteristics

Flame spread rating of 15 and smoke developed 0, when tested in accordance with ASTM E84. The core is noncombustible when tested in accordance with ASTM E136.

The 5/8" (15.9 mm) ToughRock Fireguard X Abuse-Resistant is UL classified, Type X.

* For equivalent and effective gauge steel studs, we have no evaluation or installation recommendations.

Submittal Approvals

Job Name _____

Contractor _____

Date _____

continued →

Physical Properties

Properties	ToughRock® Fireguard X™ Abuse-Resistant Gypsum Board
Thickness, nominal inches	5/8" (15.9 mm), ± 1/64" (0.4 mm)
Width, nominal	4' (1220 mm), ± 3/32" (2.4 mm)
Length, standard	8' (2440 mm) to 12' (3658 mm) ± 1/4" (6.4 mm)
Weight ¹ , lbs./sq. ft., nominal (kg/m ²)	2.8 (13.7)
Edges	Tapered edge
Flexural Strength ³ spacing, min.	
Parallel, lbf. (N)	≥46 (205)
Perpendicular, lbf. (N)	≥147 (654)
R Value ² , °F•ft ² •hr/BTU (m ² •K/W)	0.56 est. (0.10)
Nail Pull Resistance ³ , minimum, lbf. (N)	≥87 (387)
Hardness ³ , lbf. (N) (core, edges and ends)	≥15 (67)
Humidified Deflection ²	5/8" (16 mm)
Surface Burning Characteristics ⁴ (per ASTM E84)	
Flame Spread	15
Smoke Developed	0

(The core is noncombustible when tested in accordance with ASTM E136.)

¹ Represents approximate weight for design and shipping purposes. Actual weight may vary depending on manufacturing location and other factors.

² Per Gypsum Association document GA-235.

³ Specified minimum values are as defined in ASTM C1396.

⁴ Products qualify for NFPA Class A or IBC Class 1.

ToughRock® Fireguard X™ Abuse-Resistant Gypsum Board Test Results

Test	General Description of Test	Test Result Metrics	Product Test Results
Surface Abrasion Surface Damage ASTM C1629	A wire brush is cycled across the board surface. Failure is recorded as the depth of abrasion after 50 cycles. The lower the number, the better the abrasion resistance.	Surface Abrasion 1. 0.0126" (3.2 mm) 2. 0.059" (1.5 mm) 3. 0.010" (0.3 mm)	Level 2
Surface Indentation Surface Damage ASTM C1629	A 8 lb. (3.6 kg) weight is raised 9 inches, (229 mm) then dropped onto a small 5/8" (15.9 mm) round die which hits the sample. The value reported is the average of 3 or more tests.	Indentation Resistance 1. 0.150" (3.8 mm) 2. 0.100" (2.5 mm) 3. 0.050" (1.3 mm)	Level 1
Soft-Body Impact Penetration ASTM C1629	A leather bag filled with 60 lbs. (27 kg) of shot is released against the surface of the board at increasing height until failure.	Soft Body 1. 90 ft. lbs. (122 J) 2. 195 ft. lbs. (265 J) 3. 300 ft. lbs. (405 J)	Level 1



U.S.A. Georgia-Pacific Gypsum LLC
Georgia-Pacific Gypsum II LLC
Canada Georgia-Pacific Canada LP

SALES INFORMATION AND ORDER PLACEMENT

U.S.A. West: **1-800-824-7503**
Midwest: **1-800-876-4746**
South Central: **1-800-231-6060**
Southeast: **1-800-327-2344**
Northeast: **1-800-947-4497**

CANADA Canada Toll Free: **1-800-387-6823**
Quebec Toll Free: **1-800-361-0486**

TECHNICAL INFORMATION

U.S.A. and Canada: **1-800-225-6119**, www.gpgypsum.com

TRADEMARKS TOUGHROCK, FIREGUARD X and the GEORGIA-PACIFIC logo are trademarks owned by or licensed to Georgia-Pacific Gypsum LLC. Collaborative for High Performance Schools and CHPS are trademarks owned by Collaborative for High Performance Schools, Inc.

WARRANTIES, REMEDIES AND TERMS OF SALE For current warranty information for this product, please go to www.gpgypsum.com and select the product for warranty information. All sales of this product by Georgia-Pacific are subject to our Terms of Sale available at www.gpgypsum.com.

UPDATES AND CURRENT INFORMATION The information in this document may change without notice. Visit our website at www.gpgypsum.com for updates and current information.

CAUTION For product fire, safety and use information, go to www.buildgp.com/safetyinfo or call **1-800-225-6119**.

FIRE SAFETY CAUTION Passing a fire test in a controlled laboratory setting and/or certifying or labeling a product as having a one-hour, two-hour, or any other fire resistance or protection rating and, therefore, as acceptable for use in certain fire rated assemblies/systems, does not mean that either a particular assembly/system incorporating the product, or any given piece of the product itself, will necessarily provide one-hour fire resistance, two-hour fire resistance, or any other specified fire resistance or protection in an actual fire. In the event of an actual fire, you should immediately take any and all actions necessary for your safety and the safety of others without regard for any fire rating of any product or assembly/system.