



GAUGING PLASTER

General Recommendation for Use:

Use Consistency (cc/100gms)	48 - 50
Vicat Set Time (hours)	3 - 7
% Set Expansion	0.17 - 0.19
Expected Compressive Strength (PSI)	2,000

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

Base material for reformulation of interior thin coat plaster material.

For more information, call 1-888-PLASTER.