

G-P Gypsum

a Georgia-Pacific company



Resin Cast

General Recommendation for Use:

Use Consistency (cc/100gms)	62
Vicat Set Time (minutes)	23 - 27
Minimum Dry Compressive Strength (PSI)	650

*Measured at Use Consistency

*Use Consistency is G-P Gypsum's recommended lbs. of water per 100 lbs. of plaster for using this product.

Description:

Product is designed to produce lightweight, high-strength molds and must be mixed with drill motor at high speed (1760 rpm) to incorporate air cells into the mix.

For more information, call 1-888-PLASTER.